

**Description**

Double sided adhesive transparent Polyester film, also available as version 4040 D covered on both sides.

**Release paper**

Silicone-coated glassine paper on both sides, white, 90 g/ m<sup>2</sup>, Version 4040D covered with silicone-coated paper, white, 135 g/m<sup>2</sup> and 98 g/m<sup>2</sup>

**Adhesive**

Polyacrylate, permanent, neutral

**Area of use**

Mounting film for self-adhesive equipment of even surfaces

**Technical data**

<b>Thickness*</b> (without protective paper and adhesive)	12 micron
<b>Temperature resistance</b>	adhered to aluminium, -40°C to +150°C, no variation
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	11 N/25 mm
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	> +10°C

\* average

\*\* in original packaging, at 20°C and 50% relative humidity

**Attention:**

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.