

Description

This polyolefin film made from polypropylene comes in transparent and white coated with acrylic enamel for improved printability. Surface glossy (G).

Release paper

Silicone coated on one side, 135 g/m².

Adhesive

Polyacrylate, removable

Area of use

For short durability outdoor advertising. Indoor exposure is almost unlimited.

Printing method

Screen printing and offset printing are recommended. Special inks are necessary.

Technical data

Thickness* (without protective paper and adhesive)	90 micron
Dimensional stability (FINAT TM 14)	adhered to steel adhered to steel, no measurable shrinkage in cross direction, in length 0.4 mm max.
Temperature resistance***	adhered to aluminium, -40°C to +70°C, no variation
Water resistance	adhered to aluminium, after 48h/23°C no variation
Adhesive power* (FINAT TM 1, after 24h, stainless steel)	2 N/25 mm
Tensile strength (DIN EN ISO 527)	
along	min. 38 MPa
across	min. 38 MPa
Elongation at break (DIN EN ISO 527)	
along	min. 130% (transp.), min. 110% (w.)
across	min. 180% (transp.), min. 120% (w.)
Shelf life**	2 years
Application temperature	> +10°C
Service life by specialist application under vertical outdoor exposure (normal climate of Central Europe)	2 years (not printed)

* average

** in original packaging, at 20°C and 50% relative humidity

*** normal climate of Central Europe

Attention:

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.

