

**Description**

This polyolefin film made from polypropylene comes in white and transparent coated with acrylic enamel for improved printability. Gloss surface (G).

**Release paper**

Silicone coated paper on one side, 135 g/m<sup>2</sup>.

**Adhesive**

Polyacrylate, permanent

**Area of use**

For short- and medium-term outdoor advertising. Indoor exposure is almost unlimited.

**Printing method**

Screen printing and UV-offset printing are recommended. Special inks are necessary. Please ask your printing ink manufacturer for suitable inks.

**Certificates**

BS 5609 Section 2 (Sea water resistance)

**Technical Data**

<b>Thickness*</b> (without protective paper and adhesive)	90 micron
<b>Dimensional stability</b> (FINAT TM 14)	adhered to steel, no measurable shrinkage in cross direction, in length 0.4 mm max.
<b>Temperature resistance***</b>	adhered to aluminium, -40°C to +70°C, no variation
<b>Water resistance</b>	adhered to aluminium, after 48h/23°C no variation
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	12 N/25 mm
<b>Tensile strength</b> (DIN EN ISO 527)	along: min. 38 MPa across: min. 38 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	along: min. 130% (transparent), min. 110% (white) across: min. 150% (transparent), min. 120% (white)
<b>Shelf life **</b>	2 years
<b>Application temperature</b>	> 10°C
<b>Service life by specialist application</b>	2 years (not printed)
under vertical outdoor exposure (normal climate of Central Europe)	

\* average

\*\* in original packaging, at 20°C and 50% relative humidity

\*\*\* normal climate of Central Europe

**Note:**

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be dried and cured completely. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.

