

**8710****Dusted Glass Cal****Description**

Polymer PVC film for glass decoration. Its medium glossy surface inhibits undesired reflection.

**Release paper**

Silicone coated paper on one side, 137 g/m<sup>2</sup>, with special release characteristics which provide excellent waste-stripping properties.

**Adhesive**

Solvent polyacrylate, permanent

**Area of use**

Developed for the decorative designing of glass areas, to achieve a rough glass surface; especially for the designing of shop windows, room dividers and glass doors.

Suitable for manufacturing on cutting plotter systems. Wet application is recommended.

**Technical Data**

<b>Thickness*</b> (without protective paper and adhesive)	70 micron
<b>Dimensional stability</b> (FINAT TM 14)	adhered to glass, no shrinkage in cross direction, in length 0.1 mm max.
<b>Temperature resistance***</b>	adhered to aluminium, -40°C to +90°C, no variation
<b>Resistance to cleaning agents</b>	adhered to glass, 8h in washalcalics (0,5% householdcleaning agents) in room temperature and in 65°C, no variation
<b>Fire behaviour (75200)</b>	adhered to steel, self-extinguishing
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	18 N/25 mm glass 16 N/25mm acrylic glass
<b>Tensile strength</b> (DIN EN ISO 527)	along: min. 20 MPa across: min. 20 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	along: min. 130% across: min. 130%
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	> +8°C
<b>Service life by specialist application</b> under vertical outdoor exposure (normal climate of Central Europe)	7 years

\* average

\*\* in original packaging, at 20°C and 50% relative humidity

\*\*\* normal climate of Central Europe

**Note**

The glass surface to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.